



## Technical Data Sheet

### SBR-1712 ISP

**Technical Name:** Styrene Butadiene Rubber

**CAS #:** Blend

**Appearance:** Rubber

**Technical Parameters:**

	<b>Min</b>	<b>Max</b>
Mooney/ ML4	40	50
Volatile Matter		.75%
Ash		.70%
Minus D.MV.	8	
Organic Acid	4.00%	6.00%
Extractables	30.0%	35.0%
Oil	25.77%	28.77%
Bound Sty.	22.50%	24.50%

The above information has been compiled from what we believe to be credible sources. To our knowledge the information is accurate and reliable, however, it is not guaranteed. Any recommendations issued by HB Chemical personnel or literature is derived from experience and by no means should be taken as fact or construed as a recommendation to violate of any law, regulation or patent. It is the users responsibility to determine the suitability of any HB supplied material in their application. The individual conditions of each customer are well outside of our control and we cannot be held liable for its functionality and use. Please contact our office should you need specific information beyond what is supplied above. As with all Chemical usage safety precautions beyond the stated are highly recommended.

**San Francisco 1112 Col. Del Valle, Del. Benito Juarez, Mexico D.F., CP 03100 Tel: Fax:**